



NEW FORMULA • WIDER JOINTS • EASIER TO USE • STRONGER COLOUR • NEW FORMULA

Flexible COLOURED GROUT



DUNLOP® COLOURED GROUT is a flexible coloured grout for ceramic wall and floor tiles. It offers a smooth finish, is so easy to work with and is available in a wide range of fashionable colours. **DUNLOP® COLOURED GROUT** can be used in tile joints between 1mm and 8mm wide.

JOINT PREPARATION

All spacers must be removed from joints. Ensure joints are clean and free from excess adhesive. With porous tiles, dampen the joints with water (not wet) before grouting to avoid dehydration. Do not grout until the tiling has set firmly.

MIXING

The mixed material is usable for up to 1 hour at 23°C and 50% relative humidity.

1. Mix 1kg of grout with approximately 210ml of clean, drinkable water until a thick, creamy toothpaste consistency is obtained.
2. Grout may be restirred occasionally, but do not add additional water.

Note: For swimming pools and timber floors, first dilute Dunlop Primer & Additive with water (80%, 20% water) then mix.

APPLICATION

1. Prior to grouting, it is advisable to check ease of cleaning with tiles that have a textured or matt surface.
2. Work grout diagonally into the joints using a rubber squeegee. Grout small areas at a time.
3. Compact the grout firmly into the joints, minimising the amount left on the tile surface.
4. Allow grout to firm up in the joint i.e. the grout joint is no longer wet/glossy (approx. 15-30 minutes depending on weather conditions).
5. Remove excess grout from the surface of the tiles with a damp, small-pored sponge working diagonally across the joint. Rinse the sponge frequently in clean water. Use a minimum amount of water when cleaning the tile surface and smoothing the joints so as to minimise water float shade variation, efflorescence and shrinkage.
6. When grout has sufficiently hardened in the tile joints, polish the tile surface with a clean dry cloth.
7. In warm conditions, keep the grouted joints damp with clean water after hardening begins to ensure correct hydration/curing.
8. In exterior conditions it is essential to provide protection from all extremes of climate during the whole fixing and grouting operations and for as long as possible afterwards.

COVERAGE

The table below shows approximate coverage in kilograms per square metre. A 15% wastage allowance has been included due to varying application techniques, tile types and job site variations.

TILE SIZE L x W x Depth	JOINT WIDTH			
	1.5mm	3mm	5mm	8mm
25 x 25 x 4	1.10kg/m ²	2.20kg/m ²	3.70kg/m ²	5.90kg/m ²
100 x 100 x 8	0.55kg/m ²	1.10kg/m ²	1.85kg/m ²	2.95kg/m ²
200 x 200 x 8	0.30kg/m ²	0.55kg/m ²	0.90kg/m ²	1.45kg/m ²
330 x 330 x 9	0.20kg/m ²	0.40kg/m ²	0.60kg/m ²	1.00kg/m ²

DRYING TIME

Initial set is after 24 hours at 23°C and 50% relative humidity. Full cure after 14 days after which the grout joints can be sealed, immersed in water (swimming pools). Allow longer for lower temperatures, dense tiles or high relative humidity.

CLEANING

All tools should be cleaned with water immediately after use.

PACKAGING

1.5kg, 5kg and 15kg

SHELF LIFE

24 months when stored in the original unopened packaging, in a dry place at 30°C and 50% relative humidity.

CAUTION

Do not use in expansion or movement joints, use a flexible silicone. Due to varying degrees of movement inherent in timber floors, use DUNLOP® COLOURED GROUT mixed with DUNLOP® PRIMER AND ADDITIVE (refer to instructions on DUNLOP® PRIMER AND ADDITIVE). In swimming pool applications, use a white DUNLOP® COLOURED GROUT (i.e. White 200) mixed with DUNLOP® PRIMER AND ADDITIVE. The chemical balance of swimming pools must be maintained. Depending on application technique, some concavity may occur in wider joints. Test over polished marble prior to large scale grouting.

SAFETY

This product contains cement. The dust can be irritating to the skin and eyes and wet cement may cause dermatitis. Wear gloves when working and avoid inhaling dust. If the solid/dust enters the eyes, wash with clean water for at least 15 minutes and seek medical advice. If swallowed do not induce vomiting, give a glass of water and contact a doctor.

TECHNICAL DATA

Product Identity:

Form: Powder
Colour: Various

Application Properties

Mixing Ratio: 1kg powder: 210ml water
Pot Life: 1 hour

Mechanical Properties:

Compressive Strength
28 days >22 MPa

Flexural Strength (MPa):
28 days >7 MPa

Water Absorption,
30 minutes <= 3 g

Classification
(AS4992.3-2004) CG1

NFCG · 0907

TOLL FREE SERVICE:
1800 222 841(Aust) 0800 224 070 (NZ)

www.dunlopdiiy.com



Flexible

COLOURED GROUT

DUNLOP GUARANTEE

Product is guaranteed for 10 years when installed to manufacturers instructions. The guarantee does not cover shade variations and efflorescence as these are caused by factors beyond the manufacturers control, including nature of cement, job site conditions, finishing techniques and uneven drying conditions.

USER NOTES

The technical details and recommendations contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is the responsibility of the user to ensure that the products are used in accordance with DUNLOP product instructions and in applications for which they are intended.

DUNLOP is a trademark of Ansell Limited and is used under licence by ARDEX in Australia and New Zealand.

ARDEX AUSTRALIA PTY LTD. ABN 82 000 550 005
20 Powers Road, Seven Hills NSW 2147 Australia

ARDEX Australia Pty Ltd

NSW	Ph (02)9851 9100	Fax (02)9838 7970
VIC	Ph (03)9308 9255	Fax (03)9308 9332
QLD	Ph (07)3817 6000	Fax (03)3881 3188
SA	Ph (08)8268 2511	Fax (08)8345 3207
WA	Ph (08)9455 1644	Fax (08)9455 1227

ARDEX New Zealand Ltd

Auckland	Ph (09)5800 005	Fax (09)5799 963
Wellington	Ph (04)5685 949	Fax (04)5686 376
Christchurch	Ph (03)3843 029	Fax (03)3849 779

NFCG - 09/07

TOLL FREE SERVICE:
1800 222 841(Aust) 0800 224 070 (NZ)

www.dunlopdiiy.com